

Application No.: 09/678570

Case No.: 55409US002

Amendments to the Claims:

The following Listing of Claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims

1. (Currently Amended) A method of finishing brightwork on a boat for exterior exposure of the brightwork, said method comprising the steps of:

(a) providing a finishing film material in the form of a sheet, said finishing material comprising:

(i) a flexible polymeric sheet material comprising an aliphatic polyurethane, said sheet having a percent elongation of about 60% or greater, and said sheet further having a first major surface and a second major surface;

(ii) a pressure sensitive adhesive layer covering at least a portion of the first major surface of the sheet material;

(b) providing a wood substrate having a surface, wherein the wood substrate comprises the brightwork; and

(c) adhering the adhesive layer of the finishing film material to the surface of the wood by placing the adhesive layer of the finishing film in contact with the surface of the wood substrate.

2. (Original) The method of claim 1, wherein the wood substrate is selected from the group consisting of teak and mahogany.

3. (Canceled)

4. (Canceled)

Application No.: 09/678570

Case No.: 55409US002

5. (Original) The method of claim 4, wherein the polymeric sheet material has a thickness ranging from about 3 to 18 mils.
6. (Original) The method of claim 4, wherein the polymeric sheet material has a thickness ranging from about 5 to 12 mils.
7. (Original) The method of claim 1, wherein the polymeric sheet material comprises an ultraviolet absorber.
8. (Original) The method of claim 1, wherein the adhesive layer is an acrylic adhesive.
9. (Original) The method of claim 1, wherein the adhesive layer has a thickness ranging from about 0.5 to 10 mils.
10. (Original) The method of claim 1, wherein the adhesive layer has a thickness ranging from about 1 to 5 mils.
11. (Previously Presented) The method of claim 1, wherein the brightwork comprises a result of coating the surface of the wood substrate with a liquid coating composition comprising a polymer or polymer precursor dispersed or dissolved in a liquid.
12. (Previously Presented) The method of claim 11, wherein the liquid coating composition comprises an aliphatic polyurethane polymer dispersed or dissolved in a solvent.
13. (Previously Presented) The method of claim 1, further including the step of:
wetting the surface of the wood substrate with a wetting solution prior to adhering the adhesive.
14. (Original) The method of claim 1, wherein the adhesive layer is repositionable.
15. (Original) The method of claim 14, wherein the adhesive layer has a microstructured surface.

Application No.: 09/678570

Case No.: 55409US002

16. (Original) The method of claim 14, wherein the adhesive layer includes a water-soluble detachifying overcoat.

17. (Withdrawn) A method of finishing a wood surface for exterior exposure of the wood, said method comprising the steps of:

(a) providing a finishing film material in the form of a sheet, said finishing material comprising:

(i) a flexible aliphatic polyurethane sheet material having a first major surface and a second major surface;

(ii) an acrylic pressure sensitive adhesive layer covering at least a portion of the first major surface of the sheet material;

(b) providing a wood substrate having a surface;

(c) coating the surface of the wood substrate with a liquid varnish to form a coated surface;

(d) wetting the coated surface of the wood substrate with a wetting solution; and

(e) adhering the adhesive layer of the finishing film material to the coated surface of the wood substrate by placing the adhesive layer of the finishing film in contact with the coated surface of the wood substrate.

18. (Withdrawn) The method of claim 17, further comprising applying pressure and/or heat to at least a portion of the finishing film after placing the adhesive layer of the finishing film in contact with the coated surface of the wood substrate.

19. (Withdrawn) The method of claim 17, wherein the polymeric sheet material has a percent elongation of about 60% or greater.

Application No.: 09/678570

Case No.: 55409US002

20. (Withdrawn) The method of claim 17, wherein the polymeric sheet material has a thickness ranging from about 3 to 18 mils.
21. (Withdrawn) The method of claim 17, wherein the polymeric sheet material has a thickness ranging from about 5 to 12 mils.
22. (Withdrawn) The method of claim 17, wherein the polymeric sheet material comprises an ultraviolet absorber.
23. (Withdrawn) The method of claim 17, wherein the adhesive layer has a thickness ranging from about 0.5 to 10 mils.
24. (Withdrawn) The method of claim 17, wherein the adhesive layer has a thickness ranging from about 1 to 5 mils.
25. (Withdrawn) The method of claim 17, wherein the liquid varnish comprises a polyurethane polymer dispersed or dissolved in a solvent.
26. (Withdrawn) The method of claim 17, wherein the adhesive layer is repositionable.
27. (Withdrawn) The method of claim 17, wherein the adhesive layer has a microstructured surface.
28. (Withdrawn) The method of claim 17, wherein the adhesive layer includes a water-soluble detackifying overcoat.
29. (Withdrawn) The method of claim 17, wherein the step of coating the surface of the wood substrate comprises multiple applications of the liquid varnish.
30. (Withdrawn) The method of claim 17, wherein the wood substrate is provided on a boat.
31. (Withdrawn) The method of claim 17, wherein the coated surface is dried prior to the step of wetting the coated surface.

Application No.: 09/678570

Case No.: 55409US002

32. (Previously presented) The method of claim 1, wherein the brightwork is dried prior to the step of adhering.
33. (Previously presented) The method of claim 1, further comprising applying pressure and/or heat to at least a portion of the finishing film after placing the adhesive layer of the finishing film in contact with the surface of the wood substrate.
34. (Withdrawn) A method of finishing a wood surface for exterior exposure of the wood, said method comprising the steps of:
- (a) providing a finishing film material in the form of a sheet, said finishing material comprising:
 - (i) a flexible aliphatic polyurethane sheet material having a first major surface and a second major surface;
 - (ii) an acrylic pressure sensitive adhesive layer covering at least a portion of the first major surface of the sheet material;
 - (b) providing a wood substrate having a surface;
 - (c) coating the surface of the wood substrate with an oil or sealer that leaves the natural grain of the wood exposed to form a coated surface;
 - (d) wetting the coated surface of the wood substrate with a wetting solution; and
 - (e) adhering the adhesive layer of the finishing film material to the coated surface of the wood substrate by placing the adhesive layer of the finishing film in contact with the coated surface of the wood substrate.
35. (Withdrawn) The method of claim 34, wherein the coated surface is dried prior to the step of wetting the coated surface.

Application No.: 09/678570Case No.: 55409US002

36. (Withdrawn) A method of finishing a wood surface for exterior exposure of the wood, said method comprising the steps of:

(a) providing a finishing film material in the form of a sheet, said finishing material comprising:

(i) a flexible aliphatic polyurethane sheet material having a first major surface and a second major surface;

(ii) an acrylic pressure sensitive adhesive layer covering at least a portion of the first major surface of the sheet material;

(b) providing a wood substrate having a surface;

(c) coating the surface of the wood substrate with a liquid varnish to form a coated surface; and

(d) adhering the adhesive layer of the finishing film material to the coated surface of the wood substrate by placing the adhesive layer of the finishing film in contact with the coated surface of the wood substrate.

37. (Withdrawn) The method claim 36, wherein the liquid varnish is dried prior to the step of adhering.